

1. A barrier rib material containing a glass powder and a filler powder for use in a plasma display panel, wherein the filler powder comprises:

10% to 90% by mass of an alumina powder, and

the silica powder comprising:

25% to 75% by mass of a quartz glass powder.

the silica powder comprises from 25% to 75% by mass of an α -quartz powder, from 0% to 50% by mass of a cristobalite powder, and from 25% to 75% by mass of a quartz glass powder.

the silica powder comprises from 25% to 75% by mass of an α -quartz powder and from 25% to 75% by mass of a quartz glass powder.

the mass ratio of the glass powder to the filler powder is from 65 : 35 to

sub $A, >$